

# TECHNICAL HEALTH AND DATA SHEET

PRODUCT:- GREY BILGE PAINT

REFERENCE:- G/100/702

COLOUR:- GREY

FINISH:- GLOSS

TYPE:- MODIFIED LONG OIL ALKYD

TYPICAL SG:- 1.18 AT 20°C

TYPICAL VISCOSITY:- 4.5 POISE AT 25°C

TYPICAL TOTAL SOLIDS:- 63.3% BY WEIGHT

FLASH POINT:- ABOVE 32°C

RECOMMENDED THINNERS:- WHITE SPIRIT

APPLICATION:- BY BRUSH,ROLLER OR SPRAY

\*COVERAGE GUIDE:- 12 SQ. METRES/LITRE

\*DRYING TIME:- SURFACE DRY - 4 HOURS  
THROUGH DRY -12 HOURS

USES:- GENERAL BILGE PAINT

HEALTH & SAFETY:- SEE SHEET HSD 'A'

\*BY BRUSH TO A DRIED FILM THICKNESS OF 20-25 MICRONS AT 20°C.

## **Teamac® Paints**

**MANUFACTURERS OF DECORATIVE, MARINE AND INDUSTRIAL  
COATINGS**

Teal & Mackrill Limited,  
Lockwood Street, HULL. HU2 OHN  
Telephone: 01482-320194 Fax: 01482-219266

# TECHNICAL HEALTH AND DATA SHEET

PRODUCT:- BILGE PAINT RED

REFERENCE:- G/100/65

COLOUR:- RED

FINISH:- GLOSS

TYPE:- MODIFIED LONG OIL ALKYD

TYPICAL SG:- 1.18 AT 20°C

TYPICAL VISCOSITY:- 4.5 POISE AT 25°C

TYPICAL TOTAL SOLIDS:- 63.3% BY WEIGHT

FLASH POINT:- ABOVE 32°C

RECOMMENDED THINNERS:- WHITE SPIRIT

APPLICATION:- BY BRUSH,ROLLER OR SPRAY

\*COVERAGE GUIDE:- 12 SQ. METRES/LITRE

\*DRYING TIME:- SURFACE DRY - 4 HOURS  
THROUGH DRY -12 HOURS

USES:- GENERAL BILGE PAINT

HEALTH & SAFETY:- SEE SHEET HSD 'A'

\*BY BRUSH TO A DRIED FILM THICKNESS OF 20-25 MICRONS AT 20°C.

## **Teamac® Paints**

**MANUFACTURERS OF DECORATIVE, MARINE AND INDUSTRIAL  
COATINGS**

Teal & Mackrill Limited,  
Lockwood Street, HULL. HU2 OHN  
Telephone: 01482-320194 Fax: 01482-219266