



SUREGRIP DECK PAINT

532/G139/ ALL

DESCRIPTION:

Teamac Suregrip[®] is a modified alkyd, ready mixed, aggregated deck coating which provides a rough anti-slip finish when dry

RECOMMENDED USE:

Teamac Suregrip[®] is a safety coating for use INSIDE and OUTSIDE where a sure foothold is required. For foot or light truck traffic. Can be used on wood, metal, concrete, GRP and other suitably prepared surfaces.

AVAILABILITY:

1 litre. 2.5 litre and 5 litre

FINISH:

Aggregated

COLOUR:

Red, White, Black, Grey, Blue, Green, Yellow and Light Grey

TYPICAL S.G. (SPECIFIC GRAVITY):

1.35 - 1.55 @ 20 °C

VOLUME SOLIDS:

58 - 62%

WET FILM THICKNESS W.F.T

100 -150 microns

DRY FILM THICKNESS D.F.T

60 - 100 microns

EXPECTED SPREADING RATE:

6 - 10 sq.m / litre

60 - 100 micron d.f.t (based on brush application)

The practical spreading rate may be lower as this depends on factors such as the porosity and roughness of the surface to be painted and material losses during application.

TYPICAL VISCOSITY:

6.5 Poise @ 25C

FLASH POINT:

above 32 °C (closed cup)

DRYING TIME: @ RECOMMENDED D.F.T

Touch dry: 6 hours @ 20C

Hard dry: 24 hours @ 20C

Full hardness: 5 - 7 days @ 20 °C

Low temperature and high humidity will adversely affect application, drying and performance of any coating.

MINIMUM OVERCOATING TIME:

Minimum 16 hrs / overnight

APPLICATION SPECIAL CONDITIONS:

N/A

VOC CONTENT:

343 g / litre

VOC's (Volatile Organic Compounds) contribute to atmospheric pollution

APPLICATION DETAILS:

Application N/A
restrictions

Method: Brush or
short/medium
roller

Thinner Do not thin
(Max vol):

Nozzle size: N/A

Nozzle Thinners 14
pressure:

Cleaning Thinners 14
solvent:

For further advice contact Teamac Technical Services on +44(0)1482 320194

The physical constants are subject to normal manufacturing tolerances.

"COVERING OUR CUSTOMERS' NEEDS SINCE 1908"

TEAMAC

Lockwood Street, Hull HU2 0HN

Tel.: +44(0)1482 320194. Fax: +44(0)1482 219266

Email: info@teamac.co.uk

www.teamac.co.uk

SUREGRIP DECK PAINT**532/G139/ ALL**

Recoat Minimum 16 hrs
interval: / overnight

REVISION:

0

SURFACE PREPARATION:

All surfaces should be clean, dry, sound and free from contaminants.

Other surfaces have to be prepared and primed with the suitable primer for that substrate.

Existing painted surfaces - Surfaces should be cleaned, degreased and sanded to ensure an adequate "key" is produced. Remove all loose and flaking material and treat bare areas as new substrate and prepare accordingly.

MIXING INSTRUCTIONS:

Stir well before use. DO NOT USE MECHANICAL SHAKER!

APPLICATION CONDITIONS:

As dictated by normal good painting practice. In confined spaces, provide adequate ventilation during application and drying.

PRECEDING COAT:

Teamac Wood Primer on wood, Teamac Zinc Phosphate Metal Primer on ferrous metals, Teamac Deck Paint on GRP decks.

SUBSEQUENT COAT:

Teamac Suregrip® Deck Paint

REMARKS:**HEALTH AND SAFETY:**

See safety data sheet - SDS 10491

ISSUED:

20 November 2009

For further advice contact Teamac Technical Services on +44(0)1482 320194

The physical constants are subject to normal manufacturing tolerances.

"COVERING OUR CUSTOMERS' NEEDS SINCE 1908"

TEAMAC

Lockwood Street, Hull HU2 0HN

Tel.: +44(0)1482 320194. Fax: +44(0)1482 219266

Email: info@teamac.co.ukwww.teamac.co.uk